



Prime ABS 750

Prime ABS 750

Is a general purpose ABS product that has good impact strength, and good hot strength for thermoforming. It is an amorphous thermoplastic material and therefore, processes easier than some other thermoplastic materials.

Applications:

Prime ABS 750 may be used for interior applications such as appliance parts, tub and shower wall surrounds, and interior automotive trim. With the addition of a weatherable cap it may also be used in many outdoor applications.

Processing:

Prime ABS 750 is rather easy to thermoform due to its exceptional hot strength. It can be formed on wood, epoxy, ceramic and or aluminum tools. The forming temperature has a range of 300 - 350°F. For best results the mold temperature should be 150-190°F. In some cases it is necessary to dry the sheet before forming.



Prime ABS 750	Very High	High	Average
Impact Strength		*	
Low Temperature Impact Strength			*
Tensile Strength		*	
Flexural Modulus		*	
Heat Deflection Temperature		*	



A Subsidiary of ICC Industries, Inc.

Prime ABS 750

Finishing:

Parts made with Prime ABS 750 may be joined with machine screws, bolts, nuts, rivets, and spring steel fasteners. Thread cutting or thread-forming screws is an economical means of securing separate joints. Formed parts may be joined with Methylene Chloride if maximum impact strength is not required. Press and snap techniques and sonic welding may also be used for the bonding of Prime ABS 750.

Please contact your Primex Plastics representative for more information on finishing, fabricating, or the thermoforming process.

Colors, Textures and Capabilities:

Prime ABS 750 can be color matched to meet your specific requirements. Prime ABS 750 is available in Thicknesses from .030 - .400. Textures include; Calf Grain, HC, RM, Seville, Levant I, FL/HC and Diamond Plate.

Property	Test Method	Value	Unit
Specific Gravity	D-792	1.04	
Melt Flow	D-1238	1.7	g/10min
Gloss, 60° Angle	D-523	90	%
Tensile @ Yield	D-638	5,100	psi
Flexural Strength	D-790	8,000	psi
Flexural Modulus	D-790	270,000	psi
Notched Izod @ 73°F	D-256	6.3	ft-lb/in
Notched Izod @ - 40°F	D-256	2.2	ft-lb/in
Rockwell Hardness	D-785	102	R Scale
HDT @ 264 psi, Annealed	D-648	198	°F
Vicat Softening Point	D-1525	224	°F

Complies with UL 94-HB at thickness > .030 in.

Complies with FMVSS # 302 at thickness > .050 in.

Complies with FDA Regulation 21 CFR 181.32

Notice: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation of warranty that such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

www.primexplastics.com