



Prime HMWPE 1000 Swirl

Prime HMWPE 1000 Swirl:

This product consists of a HMWPE substrate with a three-color swirl cap of HMWPE. The swirl can be on one or both sides of the sheet. The thickness can be varied to suit your specific material requirements and draw ratios.

Applications:

Applications so far have consisted of playground equipment, camouflage deer blinds, canoes, and other sporting equipment.



Processing:

This is a crystalline material, therefore, good forming practices should be applied when forming this product. Forming temperature is 310-360°F. Mold temperature should be 160-200°F. Aluminum mold with grit blasted surface is preferred. The tool should be designed with a moat on the outside of the trim line. Mold shrink is .016 - .028 in/in.

Prime HMWPE 1000 Swirl	Very High	High	Average
Impact Strength	*		
Low Temperature Impact Strength	*		
Tensile Strength		*	
Flexural Modulus			*
Heat Deflection Temperature			*



A Subsidiary of ICC Industries, Inc.

Prime HMWPE 1000 Swirl

Finishing:

Prime HMWPE 1000 Swirl can be fabricated by using techniques such as; drilling, routing, punching, sawing and cutting with a die, laser or water jet. Mechanical screws and other type of fasteners can be used. The CLTE is high, therefore, movement of the part must be considered.

Please contact your Primex Plastics representative for more information on finishing, fabricating, or the thermoforming process.

Colors, Textures and Capabilities:

Prime HMWPE 1000 Swirl can be color matched to meet your specific requirements. Prime HMWPE 1000 Swirl is extruded in gauges of .100 to .300 and up to 90" in width. Textures include; Smooth or Levant II.

Property	Test Method	Value	Unit
Specific Gravity	D-1505	.949	
Melt Index	D-1238	10 HLMI	g/10min
Tensile @ Yield	D-638	3,600	psi
Ultimate Elongation	D-638	>600	%
Flexural Modulus	D-790	170,000	psi
ESCR	D-1693	>600	hrs.
Vicat Softening Point	D-525	256	°F
Brittleness Temperature	D-746	<-131	°F

Complies with FDA Regulation 21 CFR 177.1520

Complies with UL 94 HB @ > .060 in.

Complies with FMVSS # 302 @ > .060 in.

Notice: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation of warranty that such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

www.primexplastics.com