



Prime ABS Weather-X 100 is an ABS substrate with an Acrylic co-extruded cap. If requested a thin layer of Acrylic can be extruded on the back side for rigidizing. It offers good weatherability, chemical resistance, and high gloss with good DOI.



Prime ABS Weather-X 100

Prime ABS Weather-X 100	Very High	High	Avg.
Impact Strength	*		
Low Temperature Impact Strength		*	
Tensile Strength			*
Flexural Modulus		*	
Heat Deflection Temperature	*		

Property	Test Method	Value	Unit
Specific Gravity	D-792	1.05	g/cc
Melt Flow (230/10)	D-1238	6.5	g/10 min
Tensile @ Max	D-638	5940	psi
Ultimate Elongation	D-638	29	%
Flexural Modulus	D-790	290,000	psi
Notched Izod .125 in. @ 72° F	D-256	5.7	Ft-lb/in.
Heat Deflection .125 in. @ 66 psi	D-648	202	° F
Heat Deflection Temp. .125 in @264psi	D-648	185	° F
Mold Shrink		.003-.005	In./in.

Applications:

This product is ideal for outdoor applications such as marine, ATV, RV, Tub & Shower Surrounds or anything where the above characteristics are required.

Finishing:

Parts from this product may be joined with machine screws, bolts, nuts, and washers, rivets and spring steel fasteners. Thread cutting or thread-forming screws are an economical means of securing separate parts. Press and snap techniques, sonic welding and chemical bonding may also be used.

Processing:

Forming conditions for this product are:

Surface Temperature = 300-390° F

Mold Temperature = 110-185° F

Plug Temperature = 220-300° F

De-mold = 200° F

Mold Shrink = .005 - .008 in/in

Primary side of sheet should not be heated as much as the secondary side.

Colors, Textures and Capabilities:

There are many colors available, however, please check with your Primex representative for specific colors. Typically this product is smooth, however, there are several patterns available, such as haircell, calfgrain & levant.

Please contact your Primex Plastics representative for more information on finishing, fabricating, or the thermoforming process.

Notice:: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation of warranty that such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.