



# Component - Plastics

File Number: E213187

PRIMEX PLASTICS CORP  
1235 N "F" ST  
RICHMOND, IN 47374 United States



## Prime Co-Ex 2720 (r)

High Impact Polystyrene (HIPS), sheets

(r) - Virgin and regrind up to 50% by weight inclusive have the same basic material characteristics.

Flammability	Value	Test Method
Flame Rating		
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
Thermal	Value	Test Method
RTI Elec		UL 746
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Imp		UL 746
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Str		UL 746
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	