

FARAPRENE F301-45A

PRIMEX COLOR, COMPOUNDING & ADDITIVES



Faraprene F301-45A is an FDA compliant general purpose TPE which is used mainly in injection molding applications but can also be extruded in applications which do not require high levels of melt strength. This material shows good adhesion to PP and TPO's, and can be made pre-colored, natural, and black.

MECHANICAL PROPERTIES

Mechanical	Value	Unit	Method
Tensile Stress at break ^{1, 2}	650	PSI	ASTM D412
100% Tensile modulus ¹	125	PSI	ASTM D412
Elongation at break ^{1, 2}	1000	%	ASTM D412
Tear Strength ¹	120	lb/in	ASTM D624

¹ tested in cross flow direction, ² samples did not break

Physical / Rheological	Value	Unit	Method
Specific Gravity	1.17	-	ASTM D792
Melt Flow Rate, 230°C, 2.16 kg load	0.6	g/10 min	ASTM D1238
Viscosity @ 200°C & 200 s ⁻¹	190	Pa s	Internal
Hardness, 10 sec. Shore A	45	-	ASTM D2240

PROCESSING DATA

Processing Parameter

Injection Molding	Value	Unit
Melt Temperature	350-420	°F
Rear- Zone 1 Temperature	335-360	°F
Middle-Zone 2 Temperature	340-390	°F
Front- Zone 3 Temperature	350-420	°F
Nozzle Temperature	350-420	°F
Mold Temperature	70-100	°F
Backpressure	15-50	PSI
Screw Speed	50-130	RPM
Shot to Cylinder Size	50-80	%

The process conditions listed are suggested starting points and some deviations may be needed depending on the process / part design.

THESE VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES

- (1) Typical values only. Variations within normal tolerances are possible.
- (2) Only typical data for selection purposes. Not to be used for part or tool design.
- (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

DISCLAIMER: Each user bears full responsibility for making its own determination as to the suitability of each material, product, recommendation or advice set forth by Primex Color, Compounding & Additives. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Primex Color, Compounding & Additives materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Primex Color, Compounding & Additives Standard Condition of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Primex Color, Compounding & Additives. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Primex Color, Compounding & Additives or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right.

Extrusion	Value	Unit
Melt Temperature	350-420	°F
Rear Zone 1 Temperature	335-360	°F
Middle Zone 2 Temperature	340-390	°F
Front Zone 3 Temperature	350-410	°F
Adapter	350-420	°F
Head	350-420	°F
Die	350-420	°F
Screw Speed	30-60	RPM

For further information, please contact: Anthony Montalvo at amontalvo@oneilcolor.com

PRIMEX COLOR, COMPOUNDING & ADDITIVES
 Garfield, NJ 800.282.7933 Jasper, TN 800.234.6159 primexcolor.com



ISO 9001:2008
 Certified
 Management Certification
 of North America

