

Prime HMWPE 1000

Our Prime HMWPE 1000 is a high molecular weight polyethylene with excellent balance of stress crack resistance, stiffness, and melt strength.

Good rigidity and impact strength even at low temperatures. These properties make this product ideal for thermoforming large parts.

Customization

Prime HMWPE 1000 is a semi-crystalline material, so good forming practices should be used when working with this material. Forming temperature is 310–360°F. Mold temperature should be 160–200°F. Aluminum, grit blasted molds are preferred and should be designed with a moat if possible. Mold shrink is .016 to .028 in./in.

Prime HMWPE 1000 can be color matched to meet your specific requirements through our vertical integration with Primex Color, Compounding & Additives.

Sustainability

Prime HMWPE 1000 meets industry sustainability standards and can be recycled as a post-industrial or post-consumer product.

Primex Sustainability: A better tomorrow, starting today!



Prime HMWPE 1000 | Data Sheet

Prime HMWPE 1000 is available in FDA, printing, exterior construction, and thermoforming grades. Noted for their toughness, durability, and chemical resistance our polyolefins are found in a wide variety of consumer and industrial applications.

Applications

Some ideal applications for Prime HMWPE 1000 include cattle feeders, pallets, truck bed liners, portable toilets, totes, and any other parts that require the attributes mentioned above.

Finishing

Prime HMWPE 1000 can be fabricated by using techniques such as drilling, routing, punching, sawing, and cutting with a die, laser, or water jet. Mechanical screws and other type of fasteners can be used. Expansion/Contraction must be considered when working with HMWPE 1000.

Colors, Textures, and Capabilities

Prime HMWPE 1000 gauges are available from .015 up to .425 and in widths up to 169". Textures available include the following; Levant II, HC, Calf Grain, RM, and Seville.

Property	Method	Value	Unit
Specific Gravity	D792	.949	
Melt Flow	D1238	10	g/10 min
Tensile @ Yield	D638	3,600	psi
Ultimate Elongation	D638	>600	%
Flexural Modulus	D790	170,000	psi
ESCR	D1693	>600	hrs.
Brittleness Temperature	D746	<-131	°F
Vicat Softening Point	D1525	258	°F

FDA and UL compliant materials available upon request.

Prime HMWPE 1000	Very High	High	Avg.
Impact Strength	*		
Low Temperature Impact Strength	*		
Tensile Strength		*	
Flexural Modulus			*
Heat Deflection Temperature			*